

Hardness conversion table / Sertlik Dönüşüm Tablosu

Brinell Hardness (HB)	Vickers Hardness (HV)	Rockwell (HRB)	Rockwell (HRC)	UTS (N/mm ²)
–	640	–	57	–
–	615	–	56	–
–	591	–	54.5	–
–	569	–	53.5	–
–	547	–	52	–
–	528	–	51	–
–	508	–	49.5	–
–	491	–	48.5	1539
444	474	–	47	1520
429	455	–	45.5	1471
415	440	–	44.5	1422
401	425	–	43	1363
388	410	–	42	1314
375	396	–	40.5	1265
363	383	–	39	1236
352	372	–	38	1187
341	360	–	36.5	1157
331	350	–	35.5	1118
321	339	–	34.5	1089
311	328	–	33	1049
302	319	–	32	1020
293	309	–	31	990
285	301	–	30	971
277	292	–	29	941
269	284	–	27.5	912
262	276	–	26.5	892
255	269	100	25.5	873
248	261	99	24	853
241	253	98	23	824
235	247	97	22	794
229	241	96	20.5	775
223	235	–	–	755
217	228	95	–	745
212	223	94	–	716
207	218	93	–	696
197	208	91	–	667
187	197	89	–	637
179	189	87	–	608
170	179	85	–	559
163	172	83	–	539
156	165	81	–	530
149	157	79	–	500
143	150	77	–	481
137	144	74	–	471
131	138	72	–	461
126	133	69	–	451
121	127	67	–	431
116	122	64	–	422
111	117	61	–	402
107	113	–	–	382
103	108	–	–	373